

# Fill the Gaps with Quality Grout

Betonit Tile Grout is a high-quality unsanded tile joint filler consisting of cement, pigments, additives and fine sand.

## Applications

Use Betonit Tile Grout for filling joints between laid ceramic tiles, marble and granite. Best when used in conjunction with Betonit Tile Adhesives.

## Advantages

- LOW WATER ABSORPTION
- PREVENTS MOLD AND MILDEW
- ABRASION RESISTANT
- EASY TO MIX AND APPLY
- UNIFORM & NON-FADING COLORS

Exceeds requirements set by the AMERICAN NATIONAL STANDARDS INSTITUTE (ANSI)

TECHNICAL DATA (Test Method)		RESULTS
Water Absorption, 50% RH to immersion	ANSI 118.6-1999; H-4.4	< 18%
Water Absorption, Immersion to Dry	ANSI 118.6-1999; H-4.4	< 20%
Compressive Strength, 28 day cure	ANSI 118.6-1999; H-4.5	> 3000 psi
Tensile Strength, 7 day cure	ANSI 118.6-1999; H-4.6	> 250 psi
Tensile Strength, 28 day cure	ANSI 118.6-1999; H-4.6	> 350 psi
Flexural Strength, 7 day cure	ANSI 118.6-1999; H-4.4	> 400 psi

Actual performance will depend on installation methods and site conditions.

### APPROXIMATE COVERAGE PER BAG (m<sup>2</sup>)

TILE SIZE	Joint Width:	1.5mm	3mm	6mm
4.25" x 4.25"	7.5mm	4	1.5	
8" x 8"		11	5	2
12" x 12"		16	8	3
15" x 15"		21	12	4

# Betonit™

# Tile Grout

TILE JOINT FILLER

## How to use:

**SURFACE PREPARATION:** Area to be grouted must be allowed to set for one (1) day prior to grouting. Substrate must be fully cured, structurally sound, clean and free from dirt, oils or waxy films, loose materials, concrete sealers, curing compounds and other chemicals.

- Mix the grout in any non-absorbent mixing container such as plastic or steel sheet. Add and mix with enough water to the desired paste. Let the paste stand for 15 minutes then mix again.
- Slightly wet the joints of the tiles before spreading the grout. Spread the grout across the tile joints using a rubberized tool. Apply enough pressure to fill the joints uniformly. After 5 minutes drying, when grout residue begins to form a haze, wipe off the excess grout with a slightly wet sponge or cloth until the tiles are clean.
- The mixed tile grout can be used within 1 hour. Allow the grout to cure for at least one day before using the newly tiled area.
- For joint gaps greater than 6mm (1/4th inch), use Betonit Sanded Tile Grout.

## Available in 23 colors!

Charcoal	Brick Red	Maize
Dark Gray	Clay Red	Mustard
Light Gray	Old Rose	Sea Green
White*	Pink	Forest Green
Brown	Peach	Spring Green
Ocher	Beige	Powder Blue
Tan	Cream	Azul
Maroon	Yellow	* PRIMA WHITE also available

NOTE: Actual grout colors may vary from shown above

### MAINTENANCE

Betonit Tile Grout requires routine cleaning. Avoid using harsh chemicals such as muriatic acid since they can weaken and erode the grout.

PRODUCT PACKAGE SIZE:  
2kg bags

MINIMUM  
SETTING TIME

24hrs

SHELF LIFE IN  
DRY CONDITIONS

1yr  
unopened

3 Matched with clean grouting.

